



Performance Summary

- Enhanced soil + stain resistance
- Enhanced abrasion resistance
- CFFA-Healthcare-201: Certified
- Enhanced ink resistance
- Denim stain resistant
- Fluid barrier
- Bleach-solution cleanable
- Enhanced fade resistance

Environmental

- GREENGUARD Gold Certified
- LBC Red List Free
- REACH Compliant
- RoHS Compliant
- Healthier Hospitals Compliant
- No PFAS, fluorocarbons or perfluorinated compounds
- No added flame retardants
- No added antimicrobials
- Does not contain PVC
- Does not contain formaldehyde
- Formulated without Phthalates

Cleaning and Maintenance

Cleaning Code: **(W-S)** For water-based stains use water-based cleaners. For oil-based stains use solvent-based cleaners. We recommend using a professional cleaning service.

Bleach solutions of up to 10% may be used for more difficult stains.

Dye lots may vary slightly.

* This term and any corresponding data refer to the typical performance in the tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

** Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

Specifications

Content	95% Polyurethane made with Polycarbonate Resins, 5% Silicone
Finish	Advanced Soil and Stain Resistant Top Coat + ink resistance
Backing	Polyester
Weight	19.0 oz./lin. yd. ± 1.0 oz.
Width	54 inches
Roll Size	30 yards

Performance Characteristics

Abrasion Resistance** ASTM D-4157	Exceeds 100,000 double rubs - heavy duty
Adhesion ASTM D-751	Warp: 7.04 lbs. min., Fill: 6.91 lbs. min.
Break Strength CFFA-17	Warp: 139 lbs. min., Fill: 106 lbs. min.
Tear Strength CFFA-16	Warp: 12.9 lbs. min., Fill: 12.0 lbs. min.
Seam Slippage CFFA-14	Warp: 61.6 lbs. min., Fill: 65.0 lbs. min.
Colorfastness to Light AATCC-16	200 Hours, Class 5.0
Crocking AATCC-8	Dry: Class 5.0, Wet: Class 5.0
Fluid Barrier	Inherent Fluid Barrier
Hydrolytic Stability ISO 1419 (Tropical Test Method C)	Passes a minimum of 15 weeks; making it suitable for high traffic commercial environments.

Flammability*

California Technical Bulletin 117-2013 Section 1	Passed
NFPA 260	Class 1
UFAC	Class 1



Stinson®

C.F. Stinson, LLC
2849 Product Drive
Rochester Hills, MI 48309

P 800 841 6279
F 248 299 3884

cfstinson.com